


MADA LC- BEAD (J-SHAPED)

Technical Data Sheet

TDS-ACC-R27-Rev1 LC-Bead (J-Shaped) - July 2022



Product Description

Mada LC-Beads (J-Shaped) are ideal for Mada's Plasterboards of 12.5mm to 16mm thick. The finishing coats are applied up to the nib, which is blended back into the sheets.

Field of Application

Applicable in all Drywall Systems, for establishing of exact and vertically oriented edges.

Manufacturing Standards

In compliance with ASTM C1047.

Product Characteristics

Parameters	Details
Material	Galvanized Steel
Coating	Z120
Yield Strength	240MPa - 310MPa
Tensile Strength	340MPa - 420MPa
Thickness	0.40mm, 0.45mm and 0.50mm
Length	3000mm
Plasterboard Type	12.5mm, 15mm and 16mm
Standard Size (mm)	20x10 and 30x10

Handling and Storage

- Products are supplied in pack and sub-pack quantities and should be handled in accordance with the recommendations contained in Health and Safety at Work Principles and Practice..
- Metal products should be stored in an environmentally-friendly area away from airborne contaminants such as acid and salt sprays.
- People with sensitive skin conditions should seek medical advice before prolonged handling of metal products; hands should be washed before eating and for personal hygiene.
- Non-fogging goggles should be worn when cutting metal sections.

Installation Guidelines

- Hold bead firmly against corner and nail bead through small holes every on each flange.
- Make sure that staples penetrate the plasterboard.
- The height of staples should not be more than the thickness of plasterboard.
- They can also be fixed with Adhesive or screwed to pass thru the framing at 300mm centers.
- Drive all nails below nose of corner bead and tightly into flange.
- Joint compound should be covered smoothly and evenly.
- The products should not be used for purposes other than those shown on the Mada Technical Proposal.

For More Info Please [Sign In](#) or [Register](#)