

www.madagypsum.com

MADA HAND APPLIED RENDER

Technical Data Sheet



TECHNICAL DATA SHEET

Manufacturing Standards

Product Characteristics Mada Hand Applied Render is produced according to ASTM C59 / C59M and EN 13279-2 standards. Mada Hand Applied Render has been tested in accordance with ASTM C472.

- Composition: Stucco, Perlite, Light weight fillers & Adhesive to improve adhesion to base material.
- Usage: Internal walls and Ceilings at temperature $> 5^{\circ}$ C.
- Working Time: less than 45 mins.
- Base Material for Application: Brickwork, Concrete, Porous Concrete, Render.
- Thickness: 5-30mm.
- Coverage: 0.8 Kg/m²/mm.

Parameters	
Color	Grey / White
Mixing Ratio water / powder	0.4 : 1
Workability	< 45 mins
Initial Setting Time	45 mins
Final SettingTime	90 mins
Surface Hardness	$\geq 2.5 \text{ N/mm}^2$
Flexural Strength	\geq 1.0 N/mm ²
Compressive Strength	$\geq 2.0 \text{ N/mm}^2$
Adhesive Strength	≥ 0.1 N/mm ²
рН	6-8

- Mada Hand Applied Render should be protected from continuous exposure to moisture.
 Prolonged or repeated exposure to moisture may cause loss of strength. Use wooden pallets when storing product on concrete floors.
- Before mixing please ensure that the mixing equipment and bucket used are clean. Contamination from previous mixes adversely affects the setting time and strength.
- In a clean bucket, garner Mada Hand Applied Render into cool, clean water (Not Vice versa) at a ratio of 0.4 : 1 water to powder.
- Mix manually or with mixer. Allow the mixture to settle for 3-5 mins. Check the consistency of the
 mixture and slightly add more water if still thick, or more plaster if too liquid. Mix Again and repeat
 till desired viscosity is reached for optimum application.
- Skin: not irritant.Eyes: lightly irritant.
- Not flammable.
- Use eye protection (Glasses) and Gloves
- Storage: 12 months on dry environment.

Weight (kg)	25
Bags per Pallet	50

Material Packing Details

Technical Specification

Handling and Storage