

www.madagypsum.com

# MADA ROCKWOOL INSULATION

#### Technical Data Sheet

TDS-ACC-R08-Rev1 Mada Rockwool - June 2022



### TECHNICAL DATA SHEET

#### Technical Specification

Parameters	Detail
Color	Yellowish
Rigidity	Semi-Flexible
Supplier	Saudi-Rockwool, SIIMCO or other equivalent
	approved by Mada
Water vapor sorption	< 1 (Weight %) ASTM C1104
Thickness (mm)	50, 75, 100
Density (kg/m³)	40, 48, 64, 80, 100
Max. use temperature	7500C, ASTM C411
Thermal Conductivity	0.036 – 0.040 (w/mK)
NRC	0.7-1.0, ASTM C423
Flame Index	0, ASTM E84
Smoke Developed	0, ASTM E84
Fungal Resistance	Nil, ASTM C665
Packing	(1.2 x 0.6) m / Slab

## Handling and Storage

- Handling unpack material at application site to avoid unnecessary handling of product. keep work areas clean.
- Avoid unnecessary handling of scrap material and debris by placing such materials in suitable containers, whichshould be kept as close to the work area as possible.
- Ensure good ventilation. local exhaust ventilation may be required if the method of use produces dust levels which exceed applicable exposure limits.
- Avoid excessive eye and skin contact with dusts and fibers.
- Use recommended cleanup rocedures to avoid buildup of dusts and fibers in the work area.
- Material Storage keep material in original packaging until it is to be used Store material to protect against adverse conditions including precipitation.
- Health Hazard Inhalation: inhalation of dust can cause nose, throat lungs and upper respiratory tract irritation. persons exposed to dust may be forced to leave area because of nuisance conditions such as coughing, sneezing and nasal irritation. Eye Contac : direct contact will cause some mechanical irritation. Skin Contact: may cause transitory mechanical dermatitis.

**General Note** 

The products should not be used for purposes other than those shown on the Mada Technical Proposal.