

# MADA PLUS ACOUSTIC PLASTERBOARD

## Technical Data Sheet

TDS-PB-R11-Rev2 Mada Plus Acoustic - 2024



### Advantage



Light weight construction, easy & fast installation



Sound & thermal insulation



Improved strength & sag resistant



Easy finishing



Mold resistance

### Product Description

Mada Plus Acoustic Plasterboards are the lightweight solution for most standard internal wall and ceiling applications where higher acoustical properties are needed. The high purity gypsum core utilizes fiberglass for increased strength and improved sag-resistance, which is then sheeted with the highest quality paper lining for a superior finish.



# TECHNICAL DATA SHEET

## Field of Application

- Residential buildings.
- Commercial buildings.
- Hospitals.
- Airports.
- Educational settings.
- Light industrial and manufacturing projects.

## Manufacturing Standards

- Mada Plus Acoustic Plasterboards are designed and produced to ASTM C1396 / C1396M and EN 520 Type D Standards.

## Product Characteristics

- Length: Standard length is 2400mm, 2440mm & 3000mm. Special length is 1800mm to 4500mm.
- Width: 1200mm & 1220mm.
- Thickness: 12.5mm, 16mm. Special thickness: 15mm.
- Edge: Tapered, square, beveled
- Color: Ivory / Grey.

Note: For customized product requirements, contact Mada technical department.

## Technical Specification

Parameters	Applicable Standard	Plasterboard Thickness		
		12.5mm	15mm*	16mm
Weight (kg/m <sup>2</sup> )	± 0.2	11.6	13.9	13.9
Board Density (kg/m <sup>3</sup> )	Minimum	912	913	856
Flexural Strength (N) (Longitudinal)	ASTM C1396	≥ 476	≥ 585	≥ 654
	EN 520	≥ 550	≥ 650	≥ 688
Flexural Strength (N) (Transverse)	ASTM C1396	≥ 157	≥ 193	≥ 207
	EN 520	≥ 210	≥ 250	≥ 269
Nail Pull Resistance (N)	ASTM C1396	≥ 327	≥ 374	≥ 390
Asbestos (% by weight)	-	No asbestos fibers detected		

\*Special Requirements

## Test Data

Property		ASTM Test Method	Requirement	Mada Plasterboard
Noncombustibility		E136	Noncombustible	Meets
Core Hardness	Field	C473 (B)	Not less than 49 N	Meets
	End	C473 (B)	Not less than 49 N	Meets
	Edge	C473 (B)	Not less than 49 N	Meets
Flexural Strength	Transverse	C473 (B)	Not less than 157 N*	Meets
	Longitudinal	C473 (B)	Not less than 476 N*	Meets
Humidified Deflection	Wallboard	C473	Not greater than 32 mm*	Meets
	Ceiling board	C473	Not greater than 8 mm*	Meets
Nail Pull Resistance		C473 (B)	Not less than 327 N*	Meets

\* Per ASTM C1396 for 12.5mm gypsum wallboard and gypsum ceiling board



# TECHNICAL DATA SHEET

## Finishing

For the highest quality finish, we recommend Mada finishing products.

All painting products and systems must follow the recommendations and requirements outlined in the Appendices of ASTM C840. For priming, texture, paint, and wallcovering finishes, always follow manufacturer's directions for proper use.

All surfaces and applied jointing compound must completely dry, dust free, and gloss-free. Prime surfaces with an undiluted, high-solids content, interior flat latex paint, and allow to dry thoroughly before painting or applying other finishes.

Where gypsum panel walls and ceilings are subject to critical natural or artificial lighting, skimming the entire wall surface with jointing compound can improve fastener concealment. Skimming before painting will equalize the tension and suction differences between the paper and the jointing compound.

## Handling and Storage

- Mada Plus Plasterboards must be stored on a firm, dry, and structurally sound flooring assembly, using pallets or board packs to avoid direct contact with the floor and moisture sources.
- Never stack Plasterboard pallets higher than 4 pallets in height.
- Do not store other materials on top of Plasterboard pallets.
- Protect Plasterboards from direct rain, wind, sunlight, or other inclement weather conditions.

## Limitations

- Avoid exposure to sustained temperatures exceeding 52°C.
- Avoid exposure to excessive, repetitive or continuous moisture before, during and after installation. Eliminate sources of moisture immediately.

## Precautions for safe handling

- Minimize dust generation for sawing or sanding purposes in poorly ventilated areas.
- When working with individual sheets, always work from a single pallet, do not pull from stacks.
- Avoid eye contact – refer to Safety Data Sheet for hazard identifications and personal protective equipment.
- Plasterboards will not support body weight between rafters, joists, and framing members.
- Manual handling – Plasterboard sheets can be awkward without using an appropriate lifting technique. The weight of each sheet can vary based on different size and thickness factors.
- Mechanical handling – Pallet dimensions will vary, depending on the size of the plasterboards. To avoid overloading the lift truck, always check the palletized load weight provided within the weight tables.

## Conditions for safe storage, including any incompatibilities

Store on pallets supplied in dry conditions to separate product from ground surface. Always place pallets on firm level ground and ensure that stacks are both level and vertical.

Board width (mm)	Board length (mm)	Pallet stack height pack
1200	2400, 3000	4

## Material Packing Details

Thickness	12.5mm	16mm
Boards per pallet	66	54

Note: Pallet weight may vary depending on packing (protection board, spacers ...).